

Product : DMT (C TYPE 1000 KGS BRIQUETTE)

Document No : DMT-001

Revision Date : 26.01.2015

Revision : 4

Pages : 1

A. GENERAL

A-1 . Values shown below are the average test results that are performed per SASA's relevant test methods on the day of production.

A-2 . Production Date : 03.06.2018 - 04.06.2018

A-3 . lot Number : SDDM180091

A-4 . PO no : 000012 ITEM 10

A-5 . Container Number : JXJU 141325-0

A-6 . Material Number :80021

B. PROPERTIES, TEST RESULTS AND TEST METHODS

<u>Properties</u>	<u>Test Result</u>	<u>Specification</u>	<u>Test Methods</u>
B-1.Solidification Point (°C)	140,62	140.63+0,02	SASA
B-2.Acid number(mgr KOH/gr DMT)	0,019	0.03 max.	SASA
B-3.Absorbance (at 340 nm)	0,036	0.06 max.	SASA
B-4.Hazen color value(at 170°C)	10	10 max.	SASA
B-5.Ash Content ppm	6	10 max.	SASA
B-5.Volatile foreign matter (%)	0,007	0.1 max.	SASA
B-6.Stablility(170°C/4 hr.acid num. mg/KOH g)	0,021	0.03 max.	SASA
B-7.Hazen color value(170°C/4 hours)	10	10 max.	SASA
B-8.İron (as Fe in ppm)	0,54	1 max.	SASA
B-9.Purity %	99,93	99,9 min.	G.C.

LOT NUMBER IS IDENTICAL TO INVOICE NUMBER

SASA Polyester Sanayi A.S.
Yolgeçen Mah. Turhan Cemal Beriker
Bulvarı No:559 01355 Adana/Turkey
Phone: +90 322 4410053
Fax: +90 322 4410114

SASA
POLYESTER SAN. A.Ş.

